

Technical Terms & Conditions of Delivery: Picture glass.

Intention

Overview of the quality requirements and specifications for etched glass products of Berliner Glas Herbert Kubatz GmbH & Co. KG Syrgenstein.

Determination of the exact criteria for the definition, classification and evaluation of quality characteristics associated with etched glass products.

Scope

The following technical terms and conditions of delivery apply to single- and double-sided etched glass products of the brand **TEGLA® Classic New Generation**, **BG-Classic ZweiPlus**, **TEGLA® Gallery** and **TEGLA® Double Fit**.

Definition

Surface Defects

Surface defects are local defects which change the visual quality of the glass. These are point and linear/elongated defects.

Surface defects are for example scratches, chips, chafe marks and punctiform etching defects.

The designation for the number and size of surface defects is specified according to ISO 10110-7.

Etching Defects

Etching defects are areas with a modified etching structure unlike the actual etching.

Etching defects are for example bright (black) and dark (white) bands, unetched (blank) areas/points and defects due to acid inlets.

Glass Defects

Glass defects are defects that result from the manufacturing process of the float glass.

Glass defects are local defects such as bubbles, inclusions and tin spots as well as linear or elongated defects like drawmarks/-scratches and tin lines/-stains on the float side.

The conditions for evaluation of number and size of allowable glass defects are specified within DIN EN 572-2.

Defect Sizes

The definition of defect sizes according to DIN ISO 10110-7 is: defect size (mm) = square root (defect length x defect width).

For example, defect size 0.40 mm corresponds to a square with an edge length of 0.40 mm or a circle with a diameter of 0.45 mm.

Stock Sheets and Customized Sizes

Stock sheets are dimensions which are cut from (split) ribbon sizes for further processing at Berliner Glas.

Pre-cut sizes are dimensions that are cut from (split) ribbon sizes or already further processed products on customers request.

Geometry

Maximum Length and Width

The maximum size for the etching of picture glass is 2,130 x 1,250 mm.

Tolerances for Length and Width Dimension

| Glass size | Glass thickness (mm) | Tolerance (mm) |
|-------------|----------------------|----------------|
| Pre-cut | 0.55–3.15 | ±0.5 |
| Pre-cut | 4.0–6.0 | ±1.0 |
| Stock sheet | 0.55–6.0 | ±5.0 |

Further length and width tolerance requirements have to be agreed on in each case.

Tolerances for Glass Thickness

| Thickness (mm) | Tolerance (mm) | Thickness (mm) | Tolerance (mm) |
|----------------|----------------|----------------|----------------|
| 2.0 | +0.20/-0.30 | 3.15 | +0.05/-0.15 |
| 2.35 | +0.05/-0.15 | 4.0 | +0.20/-0.30 |
| 2.5 | +0.10/-0.20 | 5.0 | +0.20/-0.30 |
| 2.6 | +0.10/-0.20 | 6.0 | +0.20/-0.30 |
| 3.0 | +0.20/-0.30 | | |

Angular Tolerance for Pre-Cut Sizes

Maximum angular deviation: ±0.10°

Technical Terms & Conditions of Delivery: Picture glass.


Measuring Equipment Geometry

| Characteristic | Measuring device |
|------------------------------|------------------|
| Length/width $\leq 1,500$ mm | Calliper |
| Length/width $> 1,500$ mm | Tape measure |
| Thickness | Micrometer |
| Angle | Angulometer |

Quality

Edge Zone for Stock Sheets

For stock sheets, surface and glass defects (with exception of fracture causing edge defects) as well as deviations of optical properties within a circumferential edge zone of 20 mm (non-quality area) are unrestricted admissible.



Conditions of Evaluation


The inspection for surface and glass defects is performed under the following conditions:

| | Description |
|----------------------|---|
| Inspection equipment | Naked eye |
| Inspection in | Transmission |
| Lighting | Rear illumination with four fluorescent lamps with a length of 1,200 mm, arranged one above the other at a distance of 350 mm in front of a black background at the washing machine outlet. |
| Light intensity | Intensity of illumination 1,300–1,800 lux |

| | |
|--------------------------|--|
| Incidence angle of light | 85–90° to the evaluating area |
| Evaluation side | Blank or etched side |
| Evaluation angle | 40–90° to the evaluating surface |
| Evaluation time | The inspection time for the entire area is about ten seconds. Basically the following applies: all errors and discrepancies which are not identified within that given time will be ignored. |
| Evaluation distance | 600–800 mm from the glass surface |

Basically the following applies: all errors and discrepancies which are not identified according to the given conditions and within the given time will be ignored.

Schematic Test Assembly



Technical Terms & Conditions of Delivery: Picture glass.

Surface Defects

The following numbers and sizes of surface defects are permitted in the main area of stock sheets and on the whole area for pre-cut sizes:

| Area up to m ² | Permissible point defects max. number x max. defect size (mm) | Permissible scratches max. number x max. scratch width (mm)/ cumulated length (mm) |
|---------------------------|---|--|
| 0.04 | 1 x 1.6 | 2 x 0.15/5 |
| 0.16 | 2 x 1.6 | 2 x 0.15/10 |
| 0.36 | 3 x 1.6 | 3 x 0.15/15 |
| 0.64 | 2 x 2.5 | 4 x 0.15/20 |
| 1.00 | 3 x 2.5 | 6 x 0.15/30 |
| >1.00 | 4 x 2.5 | 8 x 0.15/40 |

- Defect sizes ≤ 1.0 mm will not be regarded
- Point defects and scratches are cumulative, i. e. point defects and scratches are allowed together
- No accumulation of surface defects allowed, definition according to ISO 10110-7
- Removable residues (dust, paper marks etc.) will not be considered as a defect

Further demands on surface quality have to be agreed on in each case.

Edge Defects

For pre-cut sizes, edge damages of a maximum length x width x depth of 2 mm x 1 mm x $\frac{1}{3}$ glass thickness are permitted.

Fracture causing edge defects are not permitted.

Properties

Gloss Measurement

For the measurement of the gloss values, Berliner Glas uses only measurement devices of the type BYK micro-TRI-gloss of the production series 4430 i. e. 4446. The measurement can be performed under an angle of 20°, 60° or 85° (measurement device geometry).¹

For the gloss measurement, the glass sheet has to be placed on a black, non-reflectant background (black felt is used at Berliner Glas) with the etched side facing frontwards. The measurement device is placed on the glass at an angle of 45° to the outer edges inside the main area.

¹ If using other measurement devices, there can be distinct deviations in the measured gloss values

Tolerances Gloss Values

| Product | Tolerance GW 20° in main area |
|-------------------------------|-------------------------------|
| BG-Classic ZweiPlus | 40 \pm 15 |
| TEGLA® Classic New Generation | 80 \pm 15 |
| TEGLA® Galerie | 100 \pm 15 |
| TEGLA® Double Fit | 80 \pm 15 |

Further demands on gloss values and their tolerances have to be agreed on in each case.

Further Optical Characteristics

Based on the raw materials, glass products have characteristic colors, these become more evident with increasing glass thickness. Therefore different color appearance is possible for the same products.

Warranty

In terms of warranty, please pay attention to our delivery and payment conditions - point 11.

Return of Rejected Goods

For the assessment of complaints, Berliner Glas can request the entire disputed goods from the customer.

The redelivery costs go at the expense of Berliner Glas. The customer has to ensure proper packaging so that the goods may not be damaged on the backhaul. Unauthorized complaints will be returned to the customer and partial transportation and sorting costs will be invoiced.

Storage Conditions

The storage of refined glass products has to be done properly, as is common in the glass industry. This includes in particular the prevention of moisture and temperature changes. Berliner Glas is not liable for damages caused by improper storage.